




DESCRIPTION			
Total thickness	EN ISO 24346 (EN 428)	mm	2.50
Thickness of wearlayer	EN ISO 24340 (EN 429)	mm	1.14
Weight	EN ISO 23997 (EN 430)	g/m ²	3090
Width of sheet	EN ISO24341 (EN 426)	cm	200
Lenght of sheet	EN ISO24341 (EN 426)	ml	20
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582 (EN 649)
European classification	EN ISO 10874 (EN 685)	classe	34 - 43
Fire rating	EN 13 501-1	classe	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with water	DIN 51 130	Classe	R10
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2
Wear group	NF 189	group	T
Type binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999 (EN 434)	%	≤ 0.40
Residual indentation	EN ISO 24343-1 (EN 433)	mm	≤ 0.10
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN 12 524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degré	≥ 6
Chemical product resistance	EN ISO 26987 (EN 423)	-	OK
Anti-bacterial activity (MRSA) (1)	ISO 22196	-	> 99% Inhibits growth
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
CE MARKING			
	EN 14041	-	
		-	

(1) The implementation of an effective cleaning regime is the bes defence against infection