





			TARALAY IMPRESSION COMFORT	TARALAY UNI COMFORT
DESCRIPTION				
Total thickness	ISO 24346 (EN 428)	mm	3.35	3.00
Wearlayer thickness	ISO 24340 (EN 429)	mm	0.65	0.65
Weight	ISO 23997 (EN 430)	g/m ²	2825	2300
Width of sheet	ISO 24341 (EN 426)	cm	200	200
Length of sheet	ISO 24341 (EN 426)	lm	25	25
CLASSIFICATION				
Norm / Product specification	-	-	EN 651	EN 651
European classification	ISO 10874 (EN 685)	class	34 - 42	34 - 42
Fire rating	EN 13501 - 1	class	Bfl-s1	Cfl-s1
Slip resistance wet	DIN 51 130	class	R10	R10
PERFORMANCES				
Type binder content	ISO 10582	-	-	-
Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.4	≤ 0.4
Residual indentation (requirement)	ISO 24343-1 (EN 433)	mm	≤ 0.2	≤ 0.2
Residual indentation (value)	ISO 24343-1 (EN 433)	mm	≈ 0.08	≈ 0.11
Castor chair test	ISO 4918 (EN 425)	-	OK	OK
Impact sound insulation	ISO 717 - 2	dB	19	17
Thermal conductivity	ISO 10456 (EN 12524)	W/(m.k)	≈ 0.25	≈ 0.25
Colour fastness	ISO 105 - B02	degree	≥ 6	≥ 6
Chemical product resistance	ISO 26987 (EN 423)	-	OK	OK
Surface treatment	-	-	Protocolsol [®] 2	Protocolsol [®]
Anti-bacterial activity (E.coli - S.aureus) ⁽¹⁾	ISO 22196	-	> 99 % inhibits growth	> 99 % inhibits growth
Antiviral activity (human coronavirus 229E)	ISO 21702	-	99.7% after 2h	99.7% after 2h
ENVIRONMENT / INDOOR AIR QUALITY				
TVOC after 28 days	ISO 16000 - 6	µg/m ³	< 10	< 10
Certification	-	-	Floorscore [®]	Floorscore [®]
CE MARKING				
	EN 14041	  		
				

(1) The implementation of an effective cleaning regime is the most important defence against infections.