

DESCRIPTION

Total thickness	ISO 24346 (EN 428)	mm	3.20
Wearlayer thickness	ISO 24340 (EN 429)	mm	0.85
Weight	ISO 23997 (EN 430)	g/m ²	2960
Width of sheet	ISO 24341 (EN 426)	cm	200
Length of sheet	ISO 24341 (EN 426)	lm	20






CLASSIFICATION

Norm / Product specification	-	-	EN 651
European classification	ISO 10874 (EN 685)	class	34 - 42
Fire rating	EN 13501 - 1	class	Bfl-s1
Slip resistance wet : ramp test with oil	DIN 51 130	class	R10

PERFORMANCES

Dimensional stability	ISO 23999 (EN 434)	%	≤ 0.4
Residual indentation	ISO 24343-1 (EN 433)	mm	≤ 0.2
Castor chair test	ISO 4918 (EN 425)	-	OK
Impact sound insulation	ISO 717 - 2	dB	16
Thermal conductivity	ISO 10456 (EN 12524)	W/(m.k)	≈ 0.25
Colour fastness	ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	SparClean®
Chemical product resistance	ISO 26987 (EN 423)	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol
Anti-bacterial activity (E.coli - S.aureus) ⁽¹⁾	ISO 22196	-	> 99% inhibits growth
TVOC after 28 days	ISO 16000 - 6	µg/m ³	< 100
Certification	-	-	Floorscore®

CE MARKING

	EN 14041	   
--	----------	---

(1) The implementation of an effective cleaning regime is the most important defence against infections.